

Acid Curing Black Matt

Product code: E/217X

Color: Black

Finish: Matt

Composition and Application Field

Black Acid Curing Matt, endowed with high solid contents. It is indicated to varnish furniture, doors, window sash frames, frames and casings where high durability and scratch resistance are required. It also has a good plasticity, good transparency and very good build.

NB: This product could be used as sealer and topcoat at the same time, because it represents a good sanding properties.

Available in the following version:

E/2170	6±1% Gloss
E/2171	12±3% Gloss
E/2172	30±5% Gloss
E/2173	50±5% Gloss
E/2174	70±5% Gloss

Product Preparation

Catalyst	by weight	by volume	with hardener
	10%	10%	E/1000

Pot Life 6hrs. at 25°C

Dilution

Spraying: Dilute with NC thinner E/600 at 25%.

Curtain Coater: Dilute with NC thinner E/600 at 20%.

Technical Characteristics

Physical Properties

Specific gravity	1.01	(± 0,025) Kg/l
* Visc. Ford	70	(± 5) Sec.
4/ 25°C		
Weight solids	52%	(± 2) Kg/Kg
Weight solids blended	48%	(± 2) Kg/Kg
Flash Point	21	grades
		centigrade

(Abel Pensky closed cup)

Application Rate 130gr/m² (per coat)

Drying @25°C

* Dust free	15 mn
Touch drying	25 mn
Interval coat	2 hrs
Deep drying	24 hrs

Dry Film Characteristics

Mechanical Characteristics

Gloss 60°	From 5 to 70 (ASTM D523/67)
Hardness	Very Good
Antiscratch	Very Good
Plasticity	Very Good
Sanding	Very Good

Surface Preparation

Good sanding for the wood before application of this product. Use sanding paper 120-150. Control the compatibility of stains eventually used. Apply the acid curing self sealer 2-3 cross coat according to the coverage required, the primer should be sanded with sanding paper 220, followed by sanding paper 400, after that apply the topcoat one to two cross coats.

Application Method

Spray gun: Use a spray gun with 1.8 mm nozzle at 3-4 atm/bar of pressure. It can be used for airless or air-mix equipments.

Curtain Coater: It is very important to keep controlled the viscosity during the application, adding thinner to compensate the solvents evaporation.

Subsequent Treatments

After drying this product, it does not need any subsequent treatment.

Note

Using this product with E/1000, it can be treated even handi-craft outdoor exposed. In this case take care to cover with varnish all the exposed parts, to prevent any type of infiltration. Only like this it is possible to have a product with good outdoor resistance, to take away in the time the defoiling of the varnish. Its most important characteristics are reduced formaldehyde emission, excellent wettability and the correct degree of conductivity for good wrapping in electrostatic application.

Packing

Available in 1 Usq, 1 Usg, 5 Usg.

Storage

If the drum is hermetically closed and well stored at 25°C, the product have 6 months of shelf-life.

The hardeners have 6 months of shelf-life.