



PRIME EP100 TG

Tropical Grade of Solvent Free Epoxy Primer

Technical Data Sheet

Composition and Application Field

PRIME EP100 TG is a high performance, two component, solvent free epoxy resin floor coating. **PRIME EP100 TG** is clear low viscosity epoxy floor primer. The cured film forms a hard coating with excellent adhesion to concrete, and certain metal surfaces.

PRIME EP100 TG complies with British standards BS 476, Part 7: 1971 and BS 5493 -1971.

Uses

PRIME EP100 TG is mainly used as a base coat for polyurethane deck floor coating system.

PRIME EP100 TG is used as a base coat for receiving an epoxy floor coating system. **PRIME EP100 TG** is used as a dust proof for concrete floors wherever high build is requested.

Advantages

- Good overlaping between concrete floor and polyurethane coating system.
- One coat application. Penetrating primer.
- High build to use shotblas. Excellent adhesion.
- Reduces bubbling and pinholes. Easy to apply by roll, brush and airless spray.

Surface Preparation

All surfaces should be clean, dry and free from dust and other contaminants. Wet substrates should be used sponge dried to remove all surface water, then dried. Treat oil or grease contamination should be removed degreaser followed by water or steam cleaning.

New concrete floors should be at least 28 days and have a moisture content of less than 5%. Excessive laitance should be removed by mechanical method. Dust and other debris should be removed by vacuum cleaning.

Old concrete floors damaged areas or surface irregularities should be repaired by using EPOMORTAR FC two component fast curing epoxy mortar (Refer to TDS).

Steel surface should be grit blasted then clean by solvent and kept to dry.

Deep spots or trowel marks should be rubbed down and remove dust and debris by vacuum cleaning then repair it by using **EPOSCREED 10** three component epoxy screed (Refer to TDS.)

Mixing

The entire contents of the hardener container should be poured into the base container and the two materials mixed thoroughly for at least 3 minutes. Use of heavy duty slow speed power drill with a jiffy mixing blade. Mix the two components in the quantities supplied taking care to ensure hardener container is scraped clean. Do not add solvent thinners at any time.

Application Method

PRIME EP100 TG is recommended to apply in one or two coats. **PRIME EP100 TG** can be applied to prepared surface using airless spray, brush or roller to receive polyurethane coating system.

Ensure that the area is completely coated, then sprinkle Silica Sand while Primer coat still in wet.

Coverage

7.0 – 8.0 m² / liter at 125 microns (WFT) in one coat

Cleaning

Tools and equipment can be cleaned immediately by using **THINERCOAT 10** organic solvent.

Package

5, 10 liter pack (including base and hardener).

Technical Properties

Mixed Density	1.20 + 0.05																				
Volume Solids ASTM D 2823-91	97% ± 3																				
Application Temperature	12 °C to 35 °C																				
Tack Free Time	2 hours at 35°C																				
Initial Hardness	20 hours at 35°C																				
Pot Life	45 minutes at 35°C																				
Full Cure	3 days at 35°C																				
Pull-Off (On concrete) ASTM D 4541-85	2.5 N/mm ² (CF)																				
Abrasion Resistance ASTM D 1044-85, CS-7 Wheel. 500 gm load	1000 cycles: < 90mg																				
Chemical Resistance:	<table> <tr> <td>Gasoline</td><td>Excellent</td></tr> <tr> <td>Petrol</td><td>Excellent</td></tr> <tr> <td>Diesel</td><td>Excellent</td></tr> <tr> <td>Engine Oil</td><td>Excellent</td></tr> <tr> <td>NaOH20%</td><td>Excellent</td></tr> <tr> <td>H₂SO₄</td><td>10%</td></tr> <tr> <td>Excellent</td><td></td></tr> <tr> <td>HCl 10%</td><td>Excellent</td></tr> <tr> <td>Acetic 5%</td><td>Excellent</td></tr> <tr> <td>Brake fluid</td><td>Excellent</td></tr> </table>	Gasoline	Excellent	Petrol	Excellent	Diesel	Excellent	Engine Oil	Excellent	NaOH20%	Excellent	H ₂ SO ₄	10%	Excellent		HCl 10%	Excellent	Acetic 5%	Excellent	Brake fluid	Excellent
Gasoline	Excellent																				
Petrol	Excellent																				
Diesel	Excellent																				
Engine Oil	Excellent																				
NaOH20%	Excellent																				
H ₂ SO ₄	10%																				
Excellent																					
HCl 10%	Excellent																				
Acetic 5%	Excellent																				
Brake fluid	Excellent																				

Storage and Shelf Life

Product should be stored at 25°C in dry conditions.
18 months in tightly closed container.

Flammability

PRIME EP100 TG is nonflammable material. **THINERCOAT 10** so do not expose to naked flames during application.

Health and Safety

The application of materials should be in good ventilation and avoid inhalation of the vapors. Use goggles and vinyl gloves. In case of contact with eyes, rinse immediately with plenty of clean water, do not use solvent and seek medical attention immediately. The product complies with environment and occupational health & safety standards ISO 14001 and OSHA 18001.